



Peran Comfort (2 – 3mm)

A matt, self-smoothing, flexible polyurethane coating ideal for a minimalist, modern and contemporary environment.

Peran Comfort is ideal for commercial environments with intensive traffic such as leisure, retail, offices, hospitals, schools.



Acoustic Resistance:
Resilient acoustic, noise reduction and sound dampening.




Soft & Comfortable:
Very soft feel underfoot, hard wearing and comfortable floor to walk on.



UV Resistance:
Offers superior UV stability in the aliphatic coating and topcoat.



Eco-Friendly & M1 Certified:
Low VOC, emissions and M1 Certified system.




Signal White
(near to RAL 9003)



Oyster White
(near to RAL 1013)



Pebble Grey
(near to RAL 7032)



Light Grey
(near to RAL 7035)

The colours and aggregates shown are examples of the design options that can be obtained with this system. Special colours will be priced on application. For a full colour chart and samples, contact your local Flowcrete office.



Technical Profile*

REACTION TO FIRE	
EN 13501-1	B _{fl} - s1
IMPACT RESISTANCE	
EN ISO 6272	IR20
TEMPERATURE RESISTANCE	
Tolerant of sustained temperatures up to 40°C	
WEAR RESISTANCE	
EN 13892-5	RWA300
BOND STRENGTH	
EN 13892-8	B2.0
ELONGATION AT BREAK	
DIN 53504	50-100%
SHORE A & D HARDNESS	
DIN 53505	Shore D - Approx. 40 Shore A - Approx. 80
RELEASE OF CORROSIVE SUBSTANCES	
SR (Synthetic resin screed)	
WATER PERMEABILITY	Nil - Karsten test (impermeable)
VOC - ISO 16000-9 & CEN/TS 16516 (EN 16402)	
Emission speed TVOC: <0.100 mg/m ² h after 28 days	
SLIP RESISTANCE** (in accordance with HSE and UKSRG guidelines)	
EN 13036-4 / BS 7976-2 (typical values for 4-S rubber slider)	Dry 56 low slip potential Wet 26 moderate slip potential
TOXICITY	Inert and harmless when cured
BS 8204-6 / FeRFA	Type 5

SPEED OF CURE***	10 °C	20 °C	30 °C
Light traffic	48 hrs	24 hrs	16 hrs
Full traffic	4 days	2 days	2 days
Full chemical cure	14 days	7 days	4 days

*These figures are typical properties achieved in laboratory tests at 20°C and at 50% Relative Humidity.

**The slipperiness of flooring materials can change significantly due to the installation process, after short periods of use, due to inappropriate maintenance, longer-term wear and/or surface contaminants (wet or dry). Textured systems are recommended to meet slip resistance value requirements for wet conditions and/or surface contaminants (wet or dry). Please contact our Technical Department for further details and specifications.

***From the application of the sealer.

For any other information please contact your local Flowcrete Technical Department.

Model Specification

Product	Peran Comfort
Finish	Matt

Preparatory work and application in accordance with manufacturer's instructions.

Products Included in This System

Standard system:	
Primer	Hydraseal DPM Natural @ 0.3 kg/m ² (2 coats for porous substrates)
Topping	Peran Comfort @ 2.6 kg/m ² for 2mm or @ 3.9 kg/m ² for 3mm
Sealer	Flowseal PU Matt (Ultra) @ 0.1 kg/m ² total for 2 coats

Medium Flexibility system:	
Primer	Hydraseal DPM Natural @ 0.3 kg/m ² (2 coats for porous substrates) Deckshield SF @ 1.0 kg/m ²
Topping	Peran Comfort @ 2.0 kg/m ² for 1.5mm
Sealer	Flowseal PU Matt (Ultra) @ 0.12 kg/m ² total for 2 coats

Detailed application instructions are available upon request.

Substrate Requirements

Concrete or screed substrate should be a minimum of 25 N/mm², free from laitance, dust and other contamination. The substrate should be dry to 75% RH in accordance with BS8204 and free from rising damp and ground water pressure. If no damp proof membrane is present Hydraseal DPM can be incorporated directly beneath the Peran Comfort system.

Installation Service

The installation should be carried out by a Flowcrete approved contractor with a

documented quality assurance scheme. Obtain details of our approved contractors by contacting our customer service team or enquiring via www.flowcrete.co.uk.

Notes

No resin system is totally colour fast and may change colour over time (exhibits a yellowing effect). Colour change depends on the UV light and heat levels present and hence the rate of change cannot be predicted. This is more noticeable in very light colours but does not compromise the product's physical or chemical resistance characteristics. We have endeavoured to adopt colours within our standard range which minimise this change. Intensively coloured products (e.g. hair colorants, medical disinfectants etc.) and plasticizer migration (e.g. from rubber tyres) can lead to irreversible discoloration in the surface.

Aftercare

Clean regularly in conjunction with a neutral detergent (or mild alkaline detergent for stubborn stains). A satin/ matt protective emulsion (e.g. TASKI Jontec Matt) may be applied to the surface of the Peran Comfort system if required, as part of the ongoing maintenance programme. In cases where cleaning companies carry out maintenance they should be instructed to use a floor polish with the same gloss factor as Flowseal PU Matt (Ultra).

Important Notes

Flowcrete products are guaranteed against defective materials and manufacture and are sold subject to our standard 'Terms and Conditions of Sale', copies of which can be obtained on request.

Any suggested practices or installation specifications for the composite floor or wall system (as opposed to individual product performance specifications) included in this communication (or any other) from Flowcrete UK Ltd constitute potential options only and do not constitute nor replace professional advice in such regard. Flowcrete UK Ltd recommends any customer seek independent advice from a qualified consultant prior to reaching any decision on design, installation or otherwise.

s. [2018.05,01]